

ABS Like Urethane

Properties	Test Method	ABS-Like
Shore Hardness Range ¹	ASTM D-2240	87 D
Color	Visual	White, Black or Light Amber ²
Elongation at Break %	ASTM D-638	2.5
Tensile Strength psi	ASTM D-638	11,000
Modulus of Elasticity psi	ASTM D-638	355,000
Izod Impact Ft-lb/inch - Notched	ASTM D-256	0.031
Heat Distortion Temperature	ASTM D-648	240 °F
Flexural Strength, psi	ASTM D-790	13,800
Flexural Modulus, psi (000)	ASTM D-790	402,000
UL Flame Retardant Rating	-	94V-O

¹ The values shown represent a sampling of available materials. Please call us to discuss your application.

² Material may be pigmented for color matching